

**HEIDELBERGCEMENT****mycem**

for better building

**DIAMOND CEMENTS,(Prop. HEIDELBERGCEMENT INDIA LTD)  
MADORA,JHANSI UNIT****TEST REPORT FOR MYCEM**

Portland Pozzolana Cement as per IS1489 (Part I):1991

REF.: DC/JHN/QA/2016/20

DATE- 26.06.2016.


WEEK NO. : 20

(13.05.16-19.05.16)

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS1489 (Part 1):1991
<b>(A) CHEMICAL COMPOSITION</b>		
(i) Loss on Ignition % by mass	2.17	5.0, Max.
(ii) Magnesia (MgO), % by mass	2.54	6.0, Max.
(iii) Sulphuric Anhydride (SO <sub>3</sub> ) % by mass	2.11	3.0, Max.
(iv) Total Chloride (Cl), % by mass	0.009	0.1, Max.
(v) Insoluble Material, % by mass	33.35	$X + 4.0 \times (100 - X) / 100$ Where $X$ is the declared % of Fly Ash in the PPC sample
<b>(B) PHYSICAL TESTING</b>		
<b>1. Fineness of Cement</b>		
Sp.Surface blaine (m <sup>2</sup> /kg)	354	300 m <sup>2</sup> /kg minimum
<b>2. Soundness</b>		
Le-Chatelier Expansion (mm)	1.00	10 mm, Max.
Autoclave Expansion (%)	0.088	0.8 %, Max.
<b>3. Setting Time</b>		
Initial (in Minutes)	170	30 minutes, Min.
Final (in Minutes)	215	600 minutes, Max.
<b>4. Compressive Strength (MPa)</b>		
(a) At 72 ± 1 Hrs.	23	16 MPa, Min.
(b) At 168 ± 2 Hrs.	33	22 MPa, Min.
(c) At 672 ± 4 Hrs.	46	33 MPa, Min.
<b>5. Drying Shrinkage (%)</b>	0.034	0.15 %, Max.
<b>6. Declared % of Fly Ash in PPC</b>	34.95	15 - 35 %

**Remarks :**

1. Temperature during testing -  $27 \pm 2^{\circ}$  c.
2. The amount of Fly Ash in the finished cement is not varying more than  $\pm 3\%$  from the declared value.
3. Portland Pozzolana Cement conforms to the requirement of IS 1489 (Part 1):1991 in all respects.



Head of Quality Control - Jhansi