

for better building

**DIAMOND CEMENTS,(Prop. HEIDELBERGCEMENT INDIA LTD)**  
**MADORA,JHANSI UNIT**  
**TEST REPORT FOR MYCEM**

Portland Pozzolana Cement as per IS1489 (Part I):1991

REF.: DC/JHN/QA/2015/05

DATE : 13.03.2015

WEEK NO. : 05

(29.01.15 - 04.02.15)

| CHARACTERISTIC   | RESULTS OBTAINED | REQUIREMENT OF IS1489 (Part 1):1991  |
|--|------------------|--|
| <b>(A) CHEMICAL COMPOSITION</b>                        |                  |  |
| (i) Loss on Ignition % by mass                         | 2.14             | 5.0, Max.  |
| (ii) Magnesia (MgO), % by mass                         | 2.54             | 6.0, Max.  |
| (iii) Sulphuric Anhydride (SO <sub>3</sub> ) % by mass | 2.15             | 3.0, Max.  |
| (iv) Total Chloride (Cl), % by mass                    | 0.009            | 0.1, Max.  |
| (v) Insoluble Material, % by mass                      | 33.20            | $\bar{X} + 4.0 \times (100 - \bar{X}) / 100$<br>Where $\bar{X}$ is the declared % of Fly Ash in the PPC sample |
| <b>(B) PHYSICAL TESTING</b>                            |                  |  |
| <b>1. Fineness of Cement</b>                           |                  |  |
| Sp.Surface blaine (m <sup>2</sup> /kg)                 | 354              | 300 m <sup>2</sup> /kg minimum   |
| <b>2. Soundness</b>                                    |                  |  |
| Le-Chatelier Expansion (mm)                            | 0.5              | 10 mm, Max.  |
| Autoclave Expansion (%)                                | 0.083            | 0.8 %, Max.  |
| <b>3. Setting Time</b>                                 |                  |  |
| Initial (in Minutes)                                   | 175              | 30 minutes, Min.   |
| Final (in Minutes)                                     | 220              | 600 minutes, Max.  |
| <b>4. Compressive Strength (MPa)</b>                   |                  |  |
| (a) At 72 ± 1 Hrs.                                     | 23               | 16 MPa, Min.   |
| (b) At 168 ± 2 Hrs.                                    | 33               | 22 MPa, Min.   |
| (c) At 672 ± 4 Hrs.                                    | 47               | 33 MPa, Min.   |
| <b>5. Drying Shrinkage (%)</b>                         | 0.034            | 0.15 %, Max.   |
| <b>6. Declared % of Fly Ash in PPC</b>                 | 34.47            | 15 - 35 %  |

**Remarks :**

1. Temperature during testing -  $27 \pm 2^{\circ}$  c.
2. The amount of Fly Ash in the finished cement is not varying more than  $\pm 3\%$  from the declared value.
3. Portland Pozzolana Cement conforms to the requirement of IS 1489 (Part 1):1991 in all respects.

  
Vice President