

HEIDELBERGCEMENT INDIA LTD, AMMASANDRA

TEST REPORT FOR MYCEM

REF.: HCIL/QA/2016/25

DATE : 25.07.2016

WEEK NO. : 25

HCIL(AMS)-QCD-F026
17-06-2016 to 23-06-2016

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS455:1989
(A) CHEMICAL COMPOSITION		
(i) Magnesia (MgO), % by mass	8.79	10.0 Maximum
(ii) Insoluble Residue, % by mass	1.70	4.0 Maximum
(iii) Sulphuric Anhydride (SO ₃) % by mass	2.25	3.0 Maximum
(iv) Sulphide Sulphur (S)	0.33	1.5 Maximum
(v) Loss on Ignition % by mass	1.88	5.0 Maximum
(vi) Total Chloride (Cl), % by mass	0.04	0.10 Maximum
(B) PHYSICAL TESTING		
1. Fineness of Cement		
Sp.Surface blaine (m ² /Kg)	336	225 m ² /kg minimum
2. Soundness		
Le-Chatelier Expansion (mm)	2.0	10 mm Maximum
Autoclave Expansion (%)	0.20	0.8 % Maximum
3. Setting Time		
Initial (in Minutes)	90	Not less than 30 minutes
Final (in Minutes)	200	Not more than 600 minutes
4. Compressive Strength (MPa)		
(a) At 72 ± 1 Hrs.	24.4	16 MPa Minimum
(b) At 168 ± 2 Hrs.	34	22 MPa Minimum
(c) At 672 ± 4 Hrs.	52.2	33 MPa Minimum

Remarks :

1. Physical Lab Temperature during testing - 27 ± 2° C
2. Portland Slag Cement conforms to the requirement of IS 455-1989 in all respects.


Mgr (QC)