

## HEIDELBERGCEMENT INDIA LTD, AMMASANDRA

### TEST REPORT FOR MYCEM

REF.: HCIL/QA/2017/13

DATE : 02.05.2017

WEEK NO. : 13

HCIL(AMS)-QCD-F026  
26-03-2017 to 01-04-2017

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS455:2015
<b>(A) CHEMICAL COMPOSITION</b>		
(i) Magnesia (MgO), % by mass	8.48	10.0 Maximum
(ii) Insoluble Residue, % by mass	1.50	4.0 Maximum
(iii) Sulphuric Anhydride (SO <sub>3</sub> ) % by mass	2.30	3.5 Maximum
(iv) Sulphide Sulphur (S)	0.32	1.5 Maximum
(v) Loss on Ignition % by mass	2.18	5.0 Maximum
(vi) Total Chloride (Cl), % by mass	0.03	0.10 Maximum
<b>(B) PHYSICAL TESTING</b>		
<b>1. Fineness of Cement</b>		
Sp.Surface blaine (m <sup>2</sup> /Kg)	338	225 m <sup>2</sup> /kg minimum
<b>2. Soundness</b>		
Le-Chatelier Expansion (mm)	1.0	10 mm Maximum
Autoclave Expansion (%)	0.18	0.8 % Maximum
<b>3. Setting Time</b>		
Initial (in Minutes)	100	Not less than 30 minutes
Final (in Minutes)	205	Not more than 600 minutes
<b>4. Compressive Strength (MPa)</b>		
(a) At 72 ± 1 Hrs.	23.6	16 MPa Minimum
(b) At 168 ± 2 Hrs.	36.4	22 MPa Minimum
(c) At 672 ± 4 Hrs.	51.4	33 MPa Minimum

**Remarks :**

1. Physical Lab Temperature during testing - 27 ± 2° C
2. Portland Slag Cement conforms to the requirement of **IS 455:2015** in all respects.

  
Mgr (QC)