HEIDELBERGCEMENT



HEIDELBERGCEMENT INDIA LTD, AMMASANDRA TEST REPORT FOR MYCEM

REF.: HCIL/QA/2015/22 DATE: 02.07.2015 HCIL(AMS)-QCD-F026

WEEK NO. : 22 28-05-2015 to 03-06-2015

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS455:1989
(4) 01/54/04/ 004/500/504		
(A) CHEMICAL COMPOSITION		
(i) Magnesia (MgO), % by mass	8.48	10.0 Maximum
(ii) Insoluble Residue, % by mass	1.60	4.0 Maximum
(iii) Sulphuric Anhydride (SO ₃) % by mass	2.60	3.0 Maximum
(iv) Sulphide Sulphur (S)	0.31	1.5 Maximum
(v) Loss on Ignition % by mass	1.79	5.0 Maximum
(vi) Total Chloride (Cl), % by mass	0.046	0.10 Maximum
(B) PHYSICAL TESTING		
1. Fineness of Cement		
Sp.Surface blaine (m²/Kg)	352	225 m ² /kg minimum
2. Soundness		
Le-Chatelier Expansion (mm)	3.0	10 mm Maximum
Autoclave Expansion (%)	0.24	0.8 % Maximum
3. Setting Time		
Initial (in Minutes)	95	Not less than 30 minutes
Final (in Minutes)	200	Not more than 600 minutes
4. Compressive Strength (MPa)		
(a) At 72 ± 1 Hrs.	24.0	16 MPa Minimum
(b) At 168 ± 2 Hrs.	34.2	22 MPa Minimum
(c) At 672 ± 4 Hrs.	51.6	33 MPa Minimum

Remarks:

- 1. Physical Lab Temperature during testing 27 ± 2° C
- 2. Portland Slag Cement conforms to the requirement of IS 455-1989 in all respects.

Mgr (QC)