## **HEIDELBERG**CEMENT



## HEIDELBERGCEMENT INDIA LTD, AMMASANDRA TEST REPORT FOR MYCEM

REF.: HCIL/QA/2018/28 DATE: 14.08.2018

HCIL(AMS)-QCD-F026

**WEEK NO.** : **28** 7/9/2018 to 7/15/2018

CHARACTERISTIC	RESULTS OBTAINED	REQUIREMENT OF IS455:2015
(A) CHEMICAL COMPOSITION		
(i) Magnesia (MgO), % by mass	5.05	10.0 Maximum
(ii) Insoluble Residue, % by mass	1.10	4.0 Maximum
(iii) Sulphuric Anhydride (SO <sub>3</sub> ) % by mass	2.60	3.5 Maximum
(iv) Sulphide Sulphur (S)	0.31	1.5 Maximum
(v) Loss on Ignition % by mass	1.99	5.0 Maximum
(vi) Total Chloride (Cl), % by mass	0.044	0.10 Maximum
(B) PHYSICAL TESTING		
1. Fineness of Cement		
Sp.Surface blaine (m²/Kg)	348	225 m <sup>2</sup> /kg minimum
2. Soundness		
Le-Chatelier Expansion (mm)	1.0	10 mm Maximum
Autoclave Expansion (%)	0.10	0.8 % Maximum
3. Setting Time		
Initial (in Minutes)	110	Not less than 30 minutes
Final (in Minutes)	215	Not more than 600 minutes
4. Compressive Strength (MPa)		
(a) At 72 ± 1 Hrs.	23.7	16 MPa Minimum
(b) At 168 ± 2 Hrs.	34.1	22 MPa Minimum
(c) At 672 ± 4 Hrs.	54.0	33 MPa Minimum

## Remarks :

- 1. Physical Lab Temperature during testing 27 ± 2° C
- 2. Portland Slag Cement conforms to the requirement of IS 455:2015 in all respects.

Mgr (QC)